





















wineo 400			wineo	
Covering type according to EN ISO 10582: Heterogeneous resilient-flooring to glue				
	wineo 400 wood	wineo 400 wood XL	wineo 400 stone	
Format	1200 x 180 mm	1505 x 235 mm	609.6 x 304.8 mm	
Product thickness	2 mm	2 mm	2 mm	
Planks, tiles / m² per box	18 / 3.89 m ²	12 / 4.24 m ²	18 / 3.34 m ²	
Boxes / m² per pallet	60 / 233.40 m ²	64 / 271.36 m ²	60 / 200.40 m ²	
Guarantee	15 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de			
Classification			Product composition	
	Utilization class 23 EN ISO 10874	Heavy-duty use in the domestic area		1 Surface sealing
	Utilization class 31 EN ISO 10874	Medium use in the commercial sector		2 Surface texture Various embossings
	Wear layer binder content EN ISO 10582	Type I		3 Wear layer Thickness 0.3 mm
	Reaction to fire EN 13501-1	B _{fl} - s1		4 Decor Decor film
	R9 Anti slip category DIN 51130	R 9		5 Base layer
	Slip resistance EN 13893	μ ≥ 0.30 - DS		6 Backing
	Anti-static properties EN 1815	≤ 2 kV		DESIGN Flooring to glue 
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time		wood – bevelled edge - 4-sides wood XL – registered embossed surface, bevelled edge – 4-sides
	Light fastness EN ISO 105-B02	Light fastness (method 2) ≥ 6		
	Residual indentation EN ISO 24343-1	≤ 0.1 mm without insulation mat ~ 0.17 mm with insulation mat silentPREMIUM		Certifications
	Thermal resistance EN 12667	≤ 0.15 (m ² K)/W		 windmüller flooring products WFP GmbH Nord-West-Ring 21 D-32832 Augustdorf  Elastischer Bodenbelag DOP-0401/0001 EN 14041:2004  Resilient Flooring to be used within a building.  ÉMISSIONS DANS L'AIR INTÉRIEUR <small>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (basses émissions)</small>  Phthalate free  factory made coated
	Impact sound reduction EN ISO 16251-1	~ 4 dB		
	Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		
Relevant information:				
<ul style="list-style-type: none"> Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C. Cleaning and care: see separate cleaning & care instruction. Technical subjects can be changed by Windmüller GmbH. 				